

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
5 June 2003 (05.06.2003)

PCT

(10) International Publication Number
WO 03/046112 A1

(51) International Patent Classification⁷: **C10G 11/18**,
B01D 53/56, B01J 23/90, 23/63

(21) International Application Number: PCT/US02/35462

(22) International Filing Date:
5 November 2002 (05.11.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
10/001,485 23 November 2001 (23.11.2001) US

(71) Applicant: **ENGELHARD CORPORATION** [US/US];
101 Wood Avenue, P.O. Box 770, Iselin, NJ 08830-0770
(US).

(72) Inventors: **KELKAR, C., P.**; 32 Shaffer Road, Bridge-
water, NJ 08807 (US). **STOCKWELL, David, M.**; 202
Ashland Road, Middlesex, NJ 08846 (US). **TAUSTER,**
Samuel; 10 Galahad Drive, Englishtown, NJ 07726 (US).

(74) Agents: **HAMPILOS, Gus, T.** et al.; Engelhard Corpora-
tion, 101 Wood Avenue, P.O. Box 770, Iselin, NJ 08830-
0770 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG,
SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ,
VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GI, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK,
TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, ML, MR, NE, SN, TD, TG).

Declaration under Rule 4.17:

— *as to applicant's entitlement to apply for and be granted a
patent (Rule 4.17(ii)) for all designations*

Published:

— *with international search report*

*For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*

(54) Title: NO_x REDUCTION COMPOSITION FOR USE IN FCC PROCESSES

(57) Abstract: A composition for controlling No_x emission during FCC processes comprises (i) an acidic oxide support, (ii) cerium oxide, (iii) a lanthanide oxide other than ceria such as praseodymium oxide, and (iv), optionally, an oxide of a metal from Groups Ib and IIb such as copper, silver and zinc.

WO 03/046112 A1

NO_x REDUCTION COMPOSITION
FOR USE IN FCC PROCESSES

BACKGROUND OF THE INVENTION

5

A major industrial problem involves the development of efficient methods for reducing the concentration of air pollutants, such as carbon monoxide, sulfur oxides and nitrogen oxides in waste gas streams which result from the processing and combustion of sulfur, carbon and nitrogen
10 containing fuels. The discharge of these waste gas streams into the atmosphere is environmentally undesirable at the sulfur oxide, carbon monoxide and nitrogen oxide concentrations that are frequently encountered in conventional operations. The regeneration of cracking catalyst, which has been deactivated by coke deposits in the catalytic
15 cracking of sulfur and nitrogen containing hydrocarbon feedstocks, is a typical example of a process which can result in a waste gas stream containing relatively high levels of carbon monoxide, sulfur and nitrogen oxides.

Catalytic cracking of heavy petroleum fractions is one of the major
20 refining operations employed in the conversion of crude petroleum oils to useful products such as the fuels utilized by internal combustion engines. In fluidized catalytic cracking processes, high molecular weight hydrocarbon liquids and vapors are contacted with hot, finely-divided, solid catalyst particles, either in a fluidized bed reactor or in an elongated
25 transfer line reactor, and maintained at an elevated temperature in a fluidized or dispersed state for a period of time sufficient to effect the desired degree of cracking to lower molecular weight hydrocarbons of the kind typically present in motor gasoline and distillate fuels.

In the catalytic cracking of hydrocarbons, some nonvolatile
30 carbonaceous material or coke is deposited on the catalyst particles. Coke comprises highly condensed aromatic hydrocarbons and generally contains from about 4 to about 10 weight percent hydrogen. When the hydrocarbon feedstock contains organic sulfur and nitrogen compounds, the coke also contains sulfur and nitrogen. As coke accumulates on the

cracking catalyst, the activity of the catalyst for cracking and the selectivity of the catalyst for producing gasoline blending stocks diminishes.

Catalyst which has become substantially deactivated through the deposit of coke is continuously withdrawn from the reaction zone. This deactivated catalyst is conveyed to a stripping zone where volatile deposits are removed with an inert gas at elevated temperatures. The catalyst particles are then reactivated to essentially their original capabilities by substantial removal of the coke deposits in a suitable regeneration process. Regenerated catalyst is then continuously returned to the reaction zone to repeat the cycle.

Catalyst regeneration is accomplished by burning the coke deposits from the catalyst surfaces with an oxygen containing gas such as air. The combustion of these coke deposits can be regarded, in a simplified manner, as the oxidation of carbon and the products are carbon monoxide and carbon dioxide.

When sulfur and nitrogen containing feedstocks are utilized in catalytic cracking process, the coke deposited on the catalyst contains sulfur and nitrogen. During regeneration of coked deactivated catalyst, the coke is burned from the catalyst surface that then results in the conversion of sulfur to sulfur oxides and nitrogen to nitrogen oxides.

The conditions experienced by the catalyst in a fluid catalytic cracking (FCC) unit are very severe. Catalyst is continuously being cycled between reductive atmosphere on the reactor side to an oxidative atmosphere on the regenerator side. The temperatures between the two zones are different so the catalyst experiences thermal shocks. Also the regenerator contains nominally about 15-25% steam. All these factors lead to a significant decline in the catalyst activity and fresh catalyst needs to be continuously added to maintain the cracking activity.

Various approaches have been used to either reduce the formation of noxious gases or treat them after they are formed. Most typically, additives have been used either as an integral part of the FCC catalyst particles or as separate particles in admixture with the FCC catalyst.

The additive that has gained the widest acceptance for lowering sulfur oxide emissions to date in FCC units (FCCU) is based upon Magnesium oxide/Magnesium aluminate/ceria technology. Pt supported on clay or alumina is most commonly used as an additive for lowering of carbon monoxide emissions. Unfortunately the additives used to control CO emissions typically cause a dramatic increase (e.g. >300%) in NO_x evolution from the regenerator.

Various approaches have been used to treat nitric oxide gases in FCCU. For example, US 5,037,538 describes the reduction of oxides of nitrogen (NO_x) emissions from an FCC regenerator by adding a deNO_x catalyst to the FCC regenerator in a form whereby the deNO_x catalyst remains segregated within the FCC regenerator.

US 5,085,762 describes the reduction of emissions of noxious nitrogen oxides with the flue gas from the regenerator of a fluid catalytic cracking plant by incorporating into the circulating inventory of cracking catalyst separate additive particles that contain a copper-loaded zeolite material having a characteristic structure with a defined X-ray diffraction pattern.


US 5,002,654 describes a process for regeneration of cracking catalyst while minimizing NO_x emissions using a zinc-based deNO_x catalyst.

US 5,021,146 describes a process for regeneration of cracking catalyst while minimizing NO_x emissions using a Group IIIb based deNO_x additive.

US 5,364,517 and US 5,364,517 describe the reduction of the NO_x content of FCC regenerator flue gas is reduced using a spinel/perovskite additive.

US 5,750,020 and US 5,591,418 describe process for removing sulfur oxides or nitrogen oxides from a gaseous mixture in an FCC process using a collapsed composition which is substantially composed of

microcrystallites collectively of the formula:



- 5 where M^{2+} is a divalent metal, M^{3+} is a trivalent metal, and T is vanadium, tungsten, or molybdenum.

US 6,165,933 describes compositions comprising a component containing (i) an acidic oxide support, (ii) an alkali metal and/or alkaline earth metal or mixtures thereof, (iii) a transition metal oxide having oxygen
10 storage capability, and (iv) palladium; to promote CO combustion in FCC processes while minimizing the formation of NO_x.

US 6,129,834 and US 6,143,167 describe compositions comprising a component containing (i) an acidic oxide support, (ii) an alkali metal and/or alkaline earth metal or mixtures thereof, (iii) a transition metal oxide
15 having oxygen storage capability, and (iv) a transition metal selected from Groups Ib and/or IIb of the Periodic Table; to provide NO_x control performance in FCC processes.

All the additives added to FCC units need to have sufficient hydrothermal stability to withstand the severe environment of an FCCU
20 and there remains the need for NO_x additives to be used in FCC that have improved hydrothermal stability.

SUMMARY OF THE INVENTION

25 The invention provides novel compositions suitable for use in FCC processes that are capable of providing improved NO_x control performance.

In one aspect, the invention provides compositions for reducing NO_x emissions in FCC processes, the compositions containing (i) an acidic
30 oxide support, (ii) ceria (iii) at least one oxide of a lanthanide series element other than ceria, and (iv), optionally, at least one oxide of a transition metal selected from Groups Ib and IIb of the Periodic Table. The acidic oxide support preferably contains alumina. Praseodymium oxide is

the preferred lanthanide oxide other than ceria. Cu and Ag are preferred Group Ib transition metals and Zn is the preferred Group IIb transition metal.

5 In another aspect, the invention encompasses FCC processes using the NO_x reduction compositions of this invention either as an integral part of the FCC catalyst particles or as separate particles admixed with the FCC catalyst.

These and other aspects of the invention are described in further detail below.

10

DETAILED DESCRIPTION OF THE INVENTION

The invention encompasses the discovery that certain classes of compositions are very effective for the reduction of NO_x gas emissions in FCC processes. Moreover, such compositions have unexpectedly improved hydrothermal stability over prior art compositions. The NO_x reduction compositions of the inventions are characterized in that they comprise (i) an acidic oxide support, (ii) cerium oxide (iii) at least one oxide of a lanthanide series element other than ceria, and (iv), optionally, at least one oxide of a transition metal selected from Groups Ib and IIb of the Periodic Table and mixtures thereof.

20 The acidic oxide support should be of sufficient acidity for the composition to act as an effective NO_x reduction additive. Acidic oxide catalyst supports are well known to those of ordinary skill in the art and include, for example, transitional aluminas such as gamma and eta alumina, silica-stabilized versions of said aluminas, including the silica-stabilized alumina spinel formed by leaching silica from kaolin calcined through its characteristic exotherm to form the spinel, or mullite. The support may be crystalline or amorphous. Preferably, the acidic oxide support contains at least some alumina. More preferably, the oxide support contains at least 50 wt. % alumina. The oxide support is preferably an oxide selected from the group consisting of alumina and silica-alumina. Where an amorphous silica-alumina support is used, the

support preferably has an alumina to silica molar ratio of from about 1:1 up to about 50:1. Examples of commercially available acidic oxide alumina supports are available under tradenames such as PURALOX, CATAPAL and VERSAL. Examples of commercially available acidic silica-alumina supports are available under the tradenames such as SIRAL and SIRALOX.

The silica-alumina support can optionally be created by the caustic leaching of silica from preformed kaolin microspheres as described in US Patents 4,847,225 and 4,628,042, which are hereby incorporated by reference for their teachings in this regard. Preferably, the kaolin that is subject to caustic leaching is calcined substantially through its characteristic exotherm to form spinel and/or mullite. More preferably, the caustic leached kaolin support is a microsphere whereby the caustic leached kaolin is bound with aluminum chlorohydroxide before calcination through the exotherm.

The acidic oxide support further preferably has sufficient surface area to facilitate the NO_x reduction process. Preferably, the oxide support has a surface area of at least about $20 \text{ m}^2/\text{g}$, more preferably from about 50 up to about $300 \text{ m}^2/\text{g}$. The acidic oxide support may be a powder which is preferable when used as an integral part of the FCC catalyst or a microsphere or particle, preferably when used as an admixture with FCC catalysts.

The amount of the cerium oxide (ceria) present in the NO_x reduction composition may be varied considerably relative to the amount of acidic oxide support. Preferably, the NO_x reduction composition contains at least about 0.5 part by weight of cerium oxide per 100 parts by weight of the acidic oxide support material, more preferably from at least about 1 part by weight up to about 25 parts by weight of cerium oxide per 100 parts of the acidic oxide support material.

The lanthanide oxides other than ceria include at least one metal oxide having oxygen storage capability similar to that of ceria. Preferably, the lanthanide oxide other than ceria is praseodymium oxide. The amount of the lanthanide oxide other than ceria present in the NO_x reduction

composition may be varied considerably relative to the amount of acidic oxide support. Preferably, the NO_x reduction composition contains from at least about 0.05 part by weight of oxide per 100 parts by weight of the acidic oxide support material, more preferably from at least about 1 part by weight up to about 25 parts by weight of lanthanide oxide other than ceria mixture per 100 parts of the acidic oxide support material. The amount of ceria to the lanthanide oxides other than ceria present in the NO_x reduction composition of this invention ranges from 1:4 to 4:1 by weight, preferably 1:2 to 2:1.

10 The Group Ib and/or IIb transition metals may be any metal or combination of metals selected from those groups of the Periodic Table. Preferably, the transition metal is selected from the group consisting of Cu, Ag, Zn and mixtures thereof. The amount of transition metal present is preferably at least about 100 parts by weight (measured as metal oxide) per million parts of the oxide support material, more preferably from about 0.1 up to about 5 parts by weight per 100 parts of the oxide support material.

20 The NO_x reduction composition may contain minor amounts of other materials, which preferably do not adversely affect the NO_x reduction function in a significant way. The NO_x reduction composition may consist essentially of items (i)-(iv) mentioned above. Where the composition of the invention is used as an additive particle for an FCC process, the NO_x reduction composition may be combined with fillers (e.g. clay, silica-alumina, silica and/or alumina particles) and/or binders (e.g. silica sol, alumina sol, silica alumina sol, etc.) to form particles suitable for use in an FCC process, preferably by spray drying before the calcination of step. More preferably, porous particles, also known as microspheres, are formed from acidic oxide support typically by spray drying powdered oxide support material combined with a binder/filler before or after impregnation with the individual constituents. Preferably, any added binders or fillers used do not significantly adversely affect the performance of the NO_x reduction component.

Where the NO_x reduction composition is used as an additive particulate (as opposed to being integrated into the FCC catalyst particles themselves), the amount of NO_x reduction component in the additive particles is preferably at least 50 wt %, more preferably at least 75 wt. %.

- 5 Most preferably, the additive particles consist entirely of the NO_x reduction component. The additive particles are preferably of a size suitable for circulation with the catalyst inventory in an FCC process. The additive particles preferably have an average particle size of about 20-200 μm. The additive particles preferably have attrition characteristics such that
- 10 they can withstand the severe environment of an FCCU.

As previously mentioned the NO_x reduction composition of the invention may be integrated into the FCC catalyst particles themselves. In such case, any conventional FCC catalyst particle components may be used in combination with the NO_x reduction composition of the invention.

- 15 If integrated into the FCC catalyst particles the NO_x reduction composition of the invention preferably represents at least about 0.02 wt. % the FCC catalyst particle, more preferably about 0.1-10 wt. %.

While the invention is not limited to any particular method of manufacture, the NO_x reduction composition of the invention is preferably

20 made by the following procedures:

- (a) co-impregnate the acidic oxide support particles with a cerium oxide source, at least one lanthanide oxide source other than ceria, and, optionally, at least one source of a Group 1b/IIb element.
- 25 (b) calcine the impregnated support of step (a).

The sources of oxides are preferably slurries, sols and/or solutions of the metal oxides themselves or salts of the respective metals, which decompose to oxides on calcination, or combinations of oxides and salts. If desired, the individual constituents may be separately added to the

30 support particles with a calcination step in between each addition. The calcination steps are preferably performed at about 450-750° C.

The NO_x reduction composition may be used as a separate additive particle or as an integral part of an FCC catalyst particle. If used as an

additive, the NO_x reduction component may itself be formed into particles suitable for use in a FCC process. Alternatively, the NO_x reduction component may be combined with binders, fillers, etc. by any conventional technique. See for example, the process described in U.S. Pat. No.

5 5,194,413, the disclosure of which is incorporated herein by reference.

Where the NO_x reduction component of the invention is integrated into an FCC catalyst particle, preferably the component is first formed and then combined with the other constituents which make up the FCC catalyst particle. Incorporation of the NO_x reduction composition directly into FCC catalyst particles may be accomplished by any known technique.

10 Examples of suitable techniques for this purpose are disclosed in U.S. Pat. Nos. 3,957,689; 4,499,197; 4,542,188 and 4,458,623, the disclosures of which are incorporated herein by reference.

The compositions of the invention may be used in any conventional FCC process. Typical FCC processes are conducted at reaction
15 temperatures of 450 to 650° C. with catalyst regeneration temperatures of 600 to 850° C. The compositions of the invention may be used in FCC processing of any typical hydrocarbon feedstocks. Preferably, the compositions of the invention are used in FCC processes involving the
20 cracking of hydrocarbon feedstocks which contain above average amounts of nitrogen, especially residual feedstocks or feedstocks having a nitrogen content of at least 0.1 wt. %. The amount of the NO_x reduction component of the invention used may vary depending on the specific FCC process. Preferably, the amount of NO_x reduction component used (in the
25 circulating inventory) is about 0.1-15 wt. % based on the weight of the FCC catalyst in the circulating catalyst inventory. The presence of the compositions of the invention during the FCC process catalyst regeneration step dramatically reduces the level of NO_x emitted during regeneration while having improved hydrothermal stability.

Example 1

2% Pr₆O₁₁/10% CeO₂/2% CuO/ Alumina

Alumina support particles are coimpregnated with a solution of cerium and
5 praseodymium nitrate by incipient wetness, dried and calcined at 1200°F
for 2 hours to achieve a 10% CeO₂ and 2 wt% Pr₆O₁₁ level. On the
microsphere, copper nitrate is impregnated, dried and calcined at 1200° F
for 2 hours to achieve a 2 wt% CuO level.

Example 2

3% La₂O₃/10% CeO₂/3% Nd₂O₃/2% CuO/ Alumina

Alumina support particles are coimpregnated with a solution of lanthanum,
cerium and neodymium nitrate by incipient wetness, dried and calcined at
15 1200°F for 2 hours to achieve a 10% CeO₂ and 2 wt% Nd₂O₃ level. On
the microsphere, copper nitrate is impregnated, dried and calcined at
1200° F for 2 hours to achieve a 2 wt% CuO level

Example 3

20 2% Pr₆O₁₁/10% CeO₂/2% CuO/Alumina

Alumina support particles are coimpregnated with a solution of cerium,
praseodymium and copper nitrate by incipient wetness, dried and calcined
at 1200°F for 2 hours to achieve a 10% CeO₂/2% Pr₆O₁₁/ 2% CuO level.

25

Example 4

2% Pr₆O₁₁/10% CeO₂/1.5% Nd₂O₃/ 2% CuO on Alumina

Alumina support particles are coimpregnated with a solution of cerium,
30 praseodymium and neodymium nitrate by incipient wetness, dried and
calcined at 1200°F for 2 hours to achieve a 10% CeO₂/10 wt% Pr₆O₁₁ 1.5%
Nd₂O₃ level. On this microsphere, copper nitrate is impregnated, dried
and calcined at 1200°F for 2 hours to achieve a 2 wt% CuO level.

COMPARATIVE EXAMPLES

Example A

5 3% Na₂O/10% CeO₂/2% CuO on Alumina

Alumina support particles are impregnated with sodium nitrate by incipient wetness, dried and calcined at 1200°F for 2 hours to achieve 3.0 wt% Na₂O. The Na-containing alumina particles are coimpregnated with a
10 solution of cerium and copper nitrate and calcined at 1200° F for 2 hours to achieve a 10 wt% CeO₂, 2% CuO level.

Example B

15 5% MgO/10% CeO₂/2% CuO Alumina

Alumina support particles are impregnated with magnesium nitrate by incipient wetness, dried and calcined at 1200°F for 2 hours to achieve a 5.0% MgO level. The Mg-containing alumina particles are coimpregnated with a solution of cerium and copper nitrate and calcined at 1200° F for 2
20 hours to achieve a 10% CeO₂, 2 wt% CuO level.

Example C

25 10% CeO₂ on Alumina

Alumina support particles are impregnated with cerium nitrate by incipient wetness, dried and calcined at 1200°F for 2 hours to achieve a 10% CeO₂ level.

Example D

30 10% Pr₆O₁₁ on Alumina

Alumina support particles are impregnated with praseodymium nitrate by incipient wetness, dried and calcined at 1200°F for 2 hours to achieve a 10% Pr₆O₁₁ level.

As previously stated hydrothermal stability is an important property of FCC catalysts and additives. Different methods are known in the art to perform accelerated hydrothermal deactivation of FCC catalysts and additives in the laboratory. The most common procedure for hydrothermal laboratory deactivation is to steam the catalyst or additive in the presence of 100% steam at temperatures ranging from 1300° to 1500°F for 4 to 8 hours. The additives tested were deactivated by steaming at 1500°F for 4 hours in 100% steam. NO uptakes were measured at room temperature on the additive after reduction in hydrogen at 1000°F. Data from NO uptake tests using Examples 1-4 and A-D are shown below in Table 1. NO uptake retention is the percentage of the NO uptake capacity retained after steaming.

Table 1

	NO uptake x 10 ⁵ Mol/g	NO uptake retention, % (As-is -Steamed)
Example A	1.39	22
Example B	1.13	28
Example C	0.75	30
Example D	0.58	32
Example 1	4.45	65
Example 2	4.9	67
Example 3	4.61	67
Example 4	3.58	64

15

As can be seen, Examples 1 through 4, within the scope of the present invention, yielded substantial NO uptake and NO uptake retention relative to Examples A and D. The results of the testing are particularly unexpected in that each of ceria and praseodymium oxide alone yielded little NO uptake (Examples C and D).

20

WE CLAIM:

1. A NO_x removal composition suitable for reducing NO_x emissions during catalyst regeneration in a fluid catalytic cracking process,
5 said composition comprising (i) an acidic oxide support, (ii) cerium oxide, (iii) at least one oxide of a lanthanide series element other than cerium oxide, and (iv), optionally, at least one oxide of a transition metal selected from Groups Ib and IIb of the Periodic Table and mixtures thereof.
- 10 2. The composition of claim 1 wherein said acidic oxide support is selected from the group consisting of alumina and silica-alumina.
3. The composition of claim 2 said acidic oxide support is alumina.
- 15 4. The composition of claim 2 wherein said acidic oxide support is silica-alumina.
5. The composition of claim 4 wherein said silica alumina has
20 an alumina:silica mole ratio of from about 1:1 up to about 50:1.
6. The composition of claim 4 wherein the said silica-alumina is prepared by caustic leaching of silica from calcined kaolin.
- 25 7. The composition of claim 4 wherein the said silica-alumina is prepared by the caustic leaching of silica from kaolin calcined through its characteristic exotherm.
8. The composition of claim 7 where the caustic leached kaolin
30 support is a microsphere whereby the caustic leached kaolin is bound with aluminum chlorohydroxide before calcination through its characteristic exotherm.

9. The composition of claim 1 wherein said Group Ib and IIb transition metals are selected from the group consisting of copper, silver, zinc and mixtures thereof.

5 10. The composition of claim 1 wherein said cerium oxide is present in amounts of from at least about 0.5 part by weight per 100 parts by weight of said acidic oxide support.

10 11. The composition of claim 1 wherein said at least one oxide of a lanthanide series element other than cerium oxide is present in amounts of at least about 0.5 part by weight per 100 parts by weight of said acidic oxide support.

15 12. The composition of claim 1 wherein said cerium oxide is present in amounts of from at least about 2 up to about 25 parts by weight per 100 parts by weight of said acidic oxide support.

20 13. The composition of claim 1 wherein said at least one oxide of a lanthanide series element other than cerium oxide is present in amounts of from at least about 2 up to about 25 parts by weight per 100 parts by weight of said acidic oxide support.

25 14. The composition of claim 1 wherein said oxide of a lanthanide series element other than cerium oxide praseodymium oxide.

15. The composition of claim 14 wherein the amount of ceria to praseodymium oxide ranges from about 1:4 to about 4:1 by weight.

30 16. The composition of claim 14 wherein the amount of ceria to praseodymium oxide ranges from about 1:2 to about 2:1 by weight.

17. A fluid cracking catalyst composition comprising (a) a cracking component suitable for catalyzing the cracking of hydrocarbons,

and (b) a NO_x reduction composition comprising (i) an acidic oxide support (ii) cerium oxide, (iii) at least one oxide of a lanthanide series element other than ceria, and (iv), optionally, an oxide of a transition metal selected from Groups Ib and IIb of the Periodic Table, said NO_x reduction composition being an integral component of the catalyst composition particles, being separate particles from the catalyst component or mixtures thereof and being present in the cracking catalyst in a sufficient NO_x reducing amount.

10 18. The cracking catalyst of claim 17 wherein said cracking catalyst comprises an admixture of component (a) and component (b).

 19. The cracking catalyst of claim 17 wherein said cracking catalyst comprises integral particles which contain both components (a)
15 and component (b).

 20. The cracking catalyst of claim 17 wherein the NO_x reduction composition (b) comprises about 0.1 to 15 wt % of the cracking catalyst composition.

20 21. The cracking catalyst of claim 17 wherein said oxide of a lanthanide series element other than ceria is praseodymium oxide.

 22. A method of reducing NO_x emission during fluid catalytic
25 cracking of a hydrocarbon feedstock into lower molecular weight components said method comprising contacting a hydrocarbon feedstock with a cracking catalyst suitable for catalyzing the cracking of hydrocarbons at elevated temperature whereby lower molecular weight hydrocarbon components are formed in the presence of a NO_x reduction
30 composition, wherein said NO_x reduction composition comprises (i) an acidic oxide support, (ii) at least 0.5 part by weight of cerium oxide per 100 parts by weight of acidic oxide support, (iii), at least one 0.5 part by weight of at least one oxide of a lanthanide series element other than ceria per

100 parts by weight of acidic oxide support and (iv), optionally, an oxide of a transition metal selected from Groups Ib and IIb of the Periodic Table, said NO_x reduction component being present in a sufficient NO_x reducing amount.

5

23. The method of claim 22 wherein said cracking catalyst and NO_x reduction composition comprises an admixture of separate the cracking catalyst component and the NO_x reduction composition component.

10

24. The method of claim 22 wherein said cracking catalyst and NO_x reduction composition comprises an integral combination of the cracking catalyst component and the NO_x reduction composition component.

15

25. The method of claim 22 wherein said cracking catalyst is fluidized during contact with a hydrocarbon feedstock.

26. The method of claim 25 further comprising recovering used cracking catalyst from said contacting step and treating said used catalyst under conditions to regenerate said catalyst.

20

27. The method of claim 22 wherein said hydrocarbon feedstock contains at least 0.1 wt % nitrogen.

25

28. The method of claim 22 wherein said at least oxide of a lanthanide series element other than ceria is praseodymium oxide.

29. The method of claim 28 wherein the amount of cerium oxide to praseodymium oxide, ranges from about 4:1 to about 1:4 by weight.

30

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 02/35462

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C10G11/18 B01D53/56 B01J23/90 B01J23/63

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C10G B01D B01J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 973 399 A (GREEN GARY J ET AL) 27 November 1990 (1990-11-27) column 14, line 49 -column 15, line 20 claim 1	1,9-14, 17,18, 20-23, 25,26,28
Y	---	6-8
X	US 4 839 026 A (BROWN STANLEY M ET AL) 13 June 1989 (1989-06-13) claims 1-4 example V; table IV	1-3, 10-14, 17,18, 20-23, 25,26,28
Y	---	6-8
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

G document member of the same patent family

Date of the actual completion of the international search

17 February 2003

Date of mailing of the international search report

26/02/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Holzwarth, A

INTERNATIONAL SEARCH REPORT

Internatⁿ application No
PCT/US 02/35462

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 981 576 A (HENSLEY JR ALBERT L ET AL) 1 January 1991 (1991-01-01) example III	1,17,19
Y	---	6-8
X	WO 00 44493 A (ENGELHARD CORP) 3 August 2000 (2000-08-03) claims 6-8 page 1, line 4 - line 14	1-4,10, 11,13-15
Y	---	6-8
X	EP 0 320 860 A (UOP INC) 21 June 1989 (1989-06-21) examples Method A, Method C claim 12	1,17,19, 21
Y	---	6-8
	US 4 847 225 A (LUSSIER ROGER J) 11 July 1989 (1989-07-11) cited in the application column 1, line 4 -column 2, line 14 column 2, line 35 - line 50 claim 6 -----	

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 02/35462

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4973399	A	27-11-1990	US 4980052 A	25-12-1990
US 4839026	A	13-06-1989	CA 1154735 A1	04-10-1983
			DE 2936718 A1	27-03-1980
			FR 2435518 A1	04-04-1980
			GB 2032947 A , B	14-05-1980
			IT 1123113 B	30-04-1986
US 4981576	A	01-01-1991	US 4224144 A	23-09-1980
			US 4306965 A	22-12-1981
			US 4476011 A	09-10-1984
			AU 532532 B2	06-10-1983
			AU 5620380 A	25-09-1980
			CA 1129839 A1	17-08-1982
			DE 3062677 D1	19-05-1983
			EP 0016599 A1	01-10-1980
			JP 1196978 C	21-03-1984
			JP 55127490 A	02-10-1980
			JP 58029141 B	21-06-1983
			US 4771027 A	13-09-1988
			US 4278566 A	14-07-1981
			US 4620922 A	04-11-1986
			US 4618594 A	21-10-1986
			AT 10068 T	15-11-1984
			AU 539917 B2	25-10-1984
			AU 7205381 A	29-04-1982
			CA 1155825 A1	25-10-1983
			DE 3166934 D1	06-12-1984
			EP 0050911 A1	05-05-1982
			JP 1632405 C	26-12-1991
			JP 2042539 B	25-09-1990
			JP 57075145 A	11-05-1982
			US 4738768 A	19-04-1988
			ZA 8104029 A	30-06-1982
WO 0044493	A	03-08-2000	US 6248688 B1	19-06-2001
			AU 2731000 A	18-08-2000
			BR 0007804 A	04-06-2002
			CN 1342101 T	27-03-2002
			EP 1171235 A1	16-01-2002
			JP 2002535135 T	22-10-2002
			WO 0044493 A1	03-08-2000
EP 0320860	A	21-06-1989	US 4855036 A	08-08-1989
			AU 2696088 A	22-06-1989
			EP 0320860 A2	21-06-1989
			FI 885832 A	19-06-1989
			JP 1308489 A	13-12-1989
US 4847225	A	11-07-1989	AU 584361 B2	25-05-1989
			AU 4823685 A	10-04-1986
			CA 1264051 A1	27-12-1989
			JP 61090736 A	08-05-1986
			US 4894143 A	16-01-1990